SE

atlas concorde USA

COLORED BODY PORCELAIN TILE

Cor	npliant with standards ANSI A137.1-2012 FIELD TILES - Available in all col	11 3/4" x 23 5/8"	FINISH	IISH MATTE		
10.00	Commercial size (in)	Nominal size (in)	Thickness (mm) Finish		Rectified Edge	
V2	12" x 24"	11 3/4" x 23 5/8"	9 mm	Matte	-	
SLIGHT VARIATION						
					1	

Clearly distinguishable differences in texture and/or pattern within similar colors.

Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish	Recuiled Edge			
12" x 24"	11 3/4" x 23 5/8"	9 mm	Matte	-			
MOSAICS AND COORDINATING TRIMS - Available in all colors							
Commercial size (in)	Nominal size (in)	Thickness (mm)	Finish				
Net Mosaic 1.5" x 2"	11 3/4" x 11 3/4"	9 mm	Matte	Please refer to caliber			
Herringbone Mosaic 1" x 4"	11 3/4" x 11 3/4"	9 mm	Matte	chart for work sizes. Close ioints			
Bullnose 3" x 24"	2 7/8" x 23 5/8"	9 mm	Matte	are not recommended.			
Cove Base 6" x 12"	5 7/8" x 11 3/4"	8.5 mm (*)	Matte	(*): Cove Base thickness is 7mm on flat part.			

PERFORMANCE & FEATURES

				Porcelain Tile Specification				
		DRODEDTY	ASTM TEST	Calibrated		Rectified		
		PROPERTY	METHOD	Minimum	Maximum	Minimum	Maximum	
		Nominal Size	ASTM C499	-3.00%	3.00%	-3.00%	2.00%	Compliant
		Caliber Range (Variation from average facial dimension of sample)		-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
REGULARITY	\searrow	Thickness ⁽¹⁾		N/A	Range: 0.40 in (1.02 mm)	N/A	Range: 0.40 in (1.02 mm)	Compliant
CHARACTERISTICS		Wedging	ASTM C502	-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.25% or -0.03 in (-0.8 mm) (*)	0.25% or 0.03 in (0.8 mm) (*)	Compliant
		Warpage Edge	ASTM C485	-0.75% or -0.09 in (-2.3 mm) (*)	0.75% or 0.09 in (2.3 mm) (*)	-0.40% or -0.05 in (-1.3 mm)(2) or -1.8 mm(3) (*)	0.40% or 0.05 in (1.3 mm)(2) or 1.8 mm(3) (*)	Compliant
		Warpage Diagonal	A3110 0403	-0.50% or -0.08 in (-2.0 mm) (*)	0.50% or 0.08 in (2.0 mm) (*)	-0.40% or -0.07 in (-1.8 mm) (*)	0.40% or 0.07 in (1.8 mm) (*)	Compliant
				All Porce	elain Tiles			
STRUCTURAL CHARACTERISTICS		Water Absorption	ASTM C373	< 0.5%				≤ 0.5%
BULK MECHANICAL CHARACTERISTICS	\downarrow	Breaking Strength	ASTM C648	Average ≥ 250 lbf. (1.11 kN) Individual ≥ 225 lbf. (1.00 kN)				≥ 350 lbf. avg
PHYSICAL PROPERTIES		Bond Strength	ASTM C482	≥ 50 psi (0.34 Mpa)				≥ 100 psi
THERMAL AND IGROMETRIC CHARACTERISTICS	ALK A	Resistance to Freeze/ Thaw Cycling	ASTM C1026	As Reported				Resistant
CHEMICAL CHARACTERISTICS		Chemical Resistance	ASTM C650	As Reported				Unaffected
		Stain Resistance	ASTM C1378	As Reported				Unaffected
SAFETY CHARACTERISTICS		Dynamic coefficient of friction	DCOF	Requires a minimum value of 0.42 for commercial areas that are likely to be wet				> 0.42 Wet

(*) Whichever is less
(1) May not apply to textured surfaces or tiles with uneven back patterns.
(2) Whichever is less, for tiles up to 24"x24" (610 mm x 610 mm).

(3) Applies to tiles larger than 24"x24" (610 mm x 610 mm).

The Health Product Declaration® logo is a registered trademark of HPD Collaborative.